

Approved Floor Coverings

Commercial Grade Sheet Vinyl

1. Inlaid commercial grade sheet vinyl with a minimum thickness of 0.085 gauge.
2. Flooring should continue up all walls, partitions, counters or cabinetry at least four inches high forming an integral 3/8 inch radius cove base.
3. All seams should be heat welded or chemically sealed to form a continuous surface.
4. Non-skid or abrasive sheet vinyl should be limited to traffic areas only.

Quarry or Ceramic Tile

1. The grout spacing between tiles should not exceed 1/4 inch and should be sealed.
2. Flooring should continue up all walls, partitions, counters or cabinetry at least four inches high forming an integral 3/8 inch radius cove base.
3. Non-skid or abrasive tiles should be limited to traffic areas only.

Troweled Epoxy Type Floor

1. Minimum finish thickness should be 3/16 inch.
2. The surface should be sealed to be impervious to water, grease and acid.
3. Flooring should continue up all walls, partitions, counters or cabinetry at least four inches high forming an integral 3/8 inch radius cove base.
4. Non-skid flooring with an abrasive texture should be limited to traffic areas only. Sanitary Cove Base and floor surface areas under equipment should be smooth.

Sealed Concrete

1. The floor should be smooth, single pour variety.
2. The floor should be sealed with a USDA approved two part catalyzed water based epoxy concrete floorsealer.
3. Concrete floors with open seams, pitted, chipped, or rough surface areas should be repaired prior to sealing concrete.
4. Flooring should continue up all walls, partitions, counters or cabinetry at least four inches high forming an integral 3/8 inch radius cove base.
5. A ceramic coved tile base may be used if keyed into floor surface so that it is flush with the sealed concrete (see image below).

FLOOR COVING

